



Henan Fuluorui New Materials Co., Ltd.

FULUORUI[®] Polycarboxylate Superplasticizer Powder

Full-Range Water-Reducing Admixture

Product Description

Polycarboxylate Superplasticizer Powder is a high performance superplasticizer prepared by special spray drying process. It has high water reducing rate and high plasticity. It has good adaptability to all kinds of cement, gypsum and other cementitious materials, has good dispersion, endows the materials with excellent workability, and makes the early strength of concrete and mortar increase rapidly, especially the late strength. It is suitable for concrete and mortar with high fluidity and high strength. This admixture meets ASTM C 494/C 494M requirements for Type A, water-reducing, and Type F, high-range water-reducing, admixtures.

Applications

Recommended for use in:

- Concrete where high flowability, high-early and ultimate strengths and increased durability are needed
- Cement based/gypsum based self leveling mortar;
- Grouting material, grouting material, special early strength mortar;
- Waterproof mortar, repair mortar and its supporting mortar;
- Bonding mortar, joint filling mortar, high strength (high fluidity) mortar, etc;
- Waterproof coating, refractory castable, pigment, cement or gypsum GRC prefabricated components, ultra high performance concrete (UHPC), etc.

Features

- Dosage flexibility for normal, mid and high-range water reduction
- Reduced water content for a given slump
- Produces cohesive and non-segregating concrete mixture
- High strength growth rate
- Providing faster setting times and strength development
- Enhanced finishability and pumpability

Benefits

Providing economic benefits to the entire construction team through higher productivity and reduced variable cost

Performance Characteristics

The dosage flexibility of FULUORUI Polycarboxylate superplasticizer powder admixture allows it to be used as a normal, mid-range and high-range water reducer.

Mixture Data: 360 kg/m³ of Type I cement; slump, 80-230 mm; non-air-entrained concrete; dosage rate adjusted to obtain 25-30% water reduction.

Setting Time

Mixture	Initial (h:min)	Difference (h:min)
Plain	4:05	-
Conventional Superplasticizer	5:35	+1:30
FULUORUI Polycarboxylate superplasticizer powder	5:05	+1:00

Compressive Strength

Mixture	3Day MPa	28Days MPa
Plain	18	32
Conventional Superplasticizer	28	48
FULUORUI Polycarboxylate superplasticizer powder	34	55

Slump Retention (mm)

Mixture	Minutes		
	Initial	30	60
Plain	90	10	0
Conventional Superplasticizer	180	160	100
FULUORUI Polycarboxylate superplasticizer powder	210	205	200

TEL: +86 13783184240 E-mail: fuluoruisales1@gmail.com

Rate of Hardening: FULUORUI polycarboxylate superplasticizer powder admixture is formulated to produce normal setting characteristics throughout its recommended dosage range. Setting time of concrete is influenced by the chemical and physical composition of the basic ingredients of the concrete, temperature of the concrete and ambient conditions. Trial mixtures should be made with actual job materials to determine the dosage required for a specified setting time and a given strength requirement.

Guidelines for Use

Dosage: The common dosage is 0.10%-0.30% (based on the total amount of cementitious materials). The best dosage shall be determined by test according to the engineering materials and characteristics. The dosage range is applicable to most mid to high-range concrete mixtures using typical concrete ingredients. However, variations in job conditions and concrete materials, such as silica fume, may require dosages outside the recommended range.

Mixing: FULUORUI Polycarboxylate superplasticizer powder admixture can be added to the mixing water during use, or added to the concrete mixer at the same time as the mixing water. It is recommended to add it to concrete and other materials after compounding. Before use, users determine the use method and conditions of the product through their own test and compounding technology.

Product Notes

Corrosivity–Non-Chloride,Non-Corrosive:

FULUORUI polycarboxylate superplasticizer powder admixture will neither initiate nor promote corrosion of reinforcing steel embedded in concrete, prestressed concrete or of galvanized steel floor and roof systems. Neither calcium chloride nor other chloride-based ingredients are used in the manufacture of FULUORUI polycarboxylate superplasticizer powder admixture.

Compatibility: FULUORUI polycarboxylate superplasticizer powder admixture is compatible with most admixtures used in the production of quality concrete, including normal, mid-range and high-range water-reducing admixtures, air-entrainers, accelerators, retarders, extended set control admixtures, corrosion inhibitors, and shrinkage reducers.

Do not use polycarboxylate superplasticizer powder admixture with admixtures containing beta-naphthalene-sulfonate. Erratic behaviors in

slump, slump flow, and pumpability may be experienced.

For directions on the proper evaluation of FULUORUI polycarboxylate superplasticizer powder admixture in specific applications, contact us.

Storage and Handling

Storage Temperature: FULUORUI polycarboxylate superplasticizer powder admixture should be stored in 10°C-40°C temperature environment, without direct sunshine, without getting wet in the rain and leaking water, without mixing impurities, without evaporation of water. If FULUORUI polycarboxylate superplasticizer powder admixture freezes, thaw at 10°C or above and completely reconstitute by mild mechanical agitation. Do not use pressurized air for agitation.

Shelf Life: FULUORUI polycarboxylate superplasticizer powder admixture has a minimum shelf life of 12 months. Depending on storage conditions, the shelf life may be greater than stated. Please contact us regarding suitability for use and dosage recommendations if the shelf life has been exceeded.

Packaging

FULUORUI polycarboxylate superplasticizer powder admixture is liquid and is packed in 1000kg IBC tank or 200Kg plastic drum.

Related Documents

Safety Data Sheets: FULUORUI polycarboxylate superplasticizer powder admixture.

Additional Information

For additional information on FULUORUI polycarboxylate superplasticizer powder admixture or its use in developing concrete mixes with special performance characteristics, contact us.

Henan Fuluorui New Materials Co.,Ltd is one of the few technology-based companies working on chemical adjuvant materials for concrete. It has strong R&D capabilities, excellent professionalism, fully automated production lines, rich application experience, and excellent reputation for the R&D, production and application of concrete admixtures and raw materials. There are nearly 500 concrete admixture manufacturers in China that have technical cooperation with our company. Fuluorui has successfully provided ODM and OEM services for customers in North America, Europe, the Middle East, Asia and other markets.

Limited Warranty Notice

FULUORUI warrants this product to be free from manufacturing defects and to meet the technical properties on the current Technical Data Guide, if

Henan Fuluorui New Materials Co., Ltd.

www.fuluoruikeji.com

FS307, Science Park, Luoyang Institute of Science and Technology, No. 90, Wangcheng Avenue, Luoyang, China 471023 Tel: +86 0379-65928516 Fax: +86 0379-65928516

TEL: +86 13783184240 E-mail: fuluoruisales1@gmail.com

used as directed within shelf life. Satisfactory results depend not only on quality products but also upon many factors beyond our control.

The Purchaser of the Product(s) must test the product(s) for suitability for the intended application and purpose before proceeding with a full application of the product(s). Performance of the product described herein should be verified by testing and carried out by qualified experts.

Henan Fuluorui New Materials Co., Ltd.

www.fuluoruikeji.com

FS307, Science Park, Luoyang Institute of Science and Technology, No. 90, Wangcheng Avenue, Luoyang, China 471023 Tel: +86 0379-65928516 Fax: +86 0379-65928516

TEL: +86 13783184240 E-mail: fuluoruisales1@gmail.com